



MP100EU

Metal Primer

DESCRIPTION

SCIGRIP® MP100EU Metal Primer is a surface treatment that is designed to clean, chemically convert and prepare stainless steel and aluminium surfaces¹ for permanent bonding with SCIGRIP Methacrylate Structural Adhesives. It significantly improves the long-term durability of adhesive bonds that are subjected to humid or corrosive environments such as salt water or salt spray. Without MP100EU, certain SCIGRIP Structural Series Adhesives can lose bond strength over time when exposed to such conditions.

MP100EU Metal Primer is recommended with SG100, SG200, SG230 HV, SG600, SG745 and SG747 for metal bonding. The SG300 and SG5000 do not require use of primer. A thin film of the metal primer is brushed or wiped on metal surfaces and allowed to dry completely before application of adhesive.

MP100EU Metal Primer is packaged in 1 litre containers (tins).

APPLICATION

MP100EU Metal Primer is applied by simply brushing or wiping on metal surfaces prior to application of adhesive. For best results use only thin coats of the primer and allow the primer to dry completely prior to application of adhesive.

PERFORMANCE BENEFITS

• Simple brush or wipe application, rapid dry	➔	Minimal added time and labour input
• Mild solvent action	➔	Cleans metal surface prior to conversion
• Aggressive etching & chemical conversion	➔	Reduces surface corrosion & chemically links adhesive to metal surface
• Red colour	➔	Simplifies application, facilitates visual inspection

TYPICAL ADHESIVE CHARACTERISTICS @ 24°C (75°F)

Physical Form	Water-thin liquid solution
Colour	Red
Density, g/cc	0.78
Density, lb/gallon	6.50
Shelf life	One Year ²
Dry Time	Fast drying (5 to 10 minutes at ambient temperatures)

NOTES:

1. Contact manufacturer for test data on specific metal substrates.
2. See "Storage and Shelf Life" on back page.

SAFETY AND HANDLING

Read Material Safety Data Sheet before handling or using this product. MP100EU Metal Primer is flammable. Always use in a well-ventilated area. Floor-level extraction and large quantities of moving air greatly facilitate ventilation. MP100EU should be stored in a cool place away from sources of heat and open flames or sparks. Keep container closed when not in use. Prevent contact with skin and eyes. In case of skin contact, wash with soap and water. In case of eye contact, flush with water for 15 minutes and seek immediate medical attention. Harmful if swallowed. Keep out of reach of children.

APPLICATION

Remove excess surface contaminants such as dust, grime, grease or oil by washing or wiping with a clean cloth. Surface should be dry before applying primer. Apply a thin coat of primer by brushing, wiping or dipping. Avoid forming puddles or heavy layers of primer. Remove excess primer by wiping while still wet, or remove with a clean rag dampened with alcohol. Re-apply if necessary to provide a thin, uniform layer.

STORAGE AND SHELF LIFE

The shelf life of MP100EU Metal Primer in unopened containers is approximately one year from the date the product is shipped from SCIGRIP facilities. Shelf life is based on steady state storage between 13°C and 27°C (55°F and 80°F). Exposure, intermittent or prolonged, above 27°C (80°F) will result in a reduction of the stated shelf life. Shelf life can be extended by air-conditioned or refrigerated storage between 10°C and 18°C (50°F and 65°F). **KEEP FROM FREEZING.**

IMPORTANT NOTES

- a. **SUBSTRATE AND APPLICATION COMPATIBILITY.** The user must determine the suitability of a selected adhesive for a given substrate and application. SCIGRIP strongly recommends laboratory, shop and end-use testing that simulates the actual manufacturing and end-use environment.
- b. **SURFACE PREPARATION.** The need for surface preparation must be determined by comparative testing of prepared and unprepared substrates to assure that unprepared bonding is equivalent to or acceptable for the application relative to prepared bonding. Initial bonding tests must be followed up with simulated or actual durability tests to assure that surface conditions do not lead to degradation of the bond over time under service conditions. Subsequent changes in substrates or bonding conditions will require re-testing.
- c. **TECHNICAL ASSISTANCE.** Contact your SCIGRIP representative for questions or assistance with the selection of adhesives and methods for evaluating adhesives for your intended application.

NOTE: *This product is intended for use by skilled individuals at their own risk. Recommendations contained herein are based on information we believe to be reliable. The properties presented above are typical values obtained under controlled conditions at the SCIGRIP laboratory. They are intended to be used only as a guide for selection for end-use evaluation. The ultimate suitability for any intended application must be verified by the end user under anticipated test conditions. Since specific use, materials and product handling are not controlled by SCIGRIP, our warranty is limited to the replacement of defective SCIGRIP products.*